



FIRTH MASONRY - WALL DENSITIES

Per manufacturing location

		Block	Grout	Fully Grouted	Gouted - 600 crs	Ungouted
		kg	kg	kg/m ²	kg/m ²	kg/m ²
15 Series	1516					
Auckland		9.8	10.3	271	181	132
Mt.Maunganui		9.2	10.3	263	173	124
Wellington		9.7	10.3	270	180	131
Napier		10.1	10.3	275	185	136
ChCh/Nelson		12.5	10.3	308	217	169
20 Series	2016					
Auckland		12.5	15	371	240	169
Mt.Maunganui		11.6	15	359	227	157
Wellington		12	15	365	233	162
Napier		12.6	15	373	241	170
ChCh/Nelson		15	15	405	273	203
25 Series	2516					
Auckland		13.8	21	470	286	186
Mt.Maunganui		12.8	21	456	272	173
Wellington		13.2	21	462	277	178
Napier		13.9	21	471	287	188
ChCh/Nelson		16.4	21	505	321	221